



GLOBAL INDUSTRY CLAY

KAOLEN	TR-19	UA-22
SiO ₂	68	67
Al ₂ O ₃	19 min	22 min
Fe ₂ O ₃	1.2 max	0.80 max
TiO ₂	1.0 max	0.60 max
CaO	0.90 max	0.80 max
MgO	0.50 max	0.50 max
Na ₂ O	1.20 max	1.00 max
K ₂ O	2.50 max	2.00 max
L.	78 min	86 min
a.	-	-
b.	-	-
Kuru Mukavemet	50 min	40 min
Yogunluk	1500	1450
Viskozite	25"	25"

info@globalclay.com.tr

Kalite odaklı üretim

